

BODY 950 SPRAY - UNDERBODY PROTECTION

Technical Data Sheet No 805



VOC compliant with the regulations

A combination of caoutchouc/ synthetic resin which has excelent adhesion

It can be painted over immediately wet on wet using synthetic paints or with one or two component acrylic paints, after drying

Remains permanently elastic

Fast drying

Provides scratch and stone chip protection

General Technical Description

2-3 passes

Dust free 10min at 23 °C

Surface

Inside bottom parts of the car body

Outside bottom parts of the car bodv

Pretreatment / Cleaning of substrate



Clean substrate using a soft cloth and BODY 770 ANTISIL NORMAL / BODY 771 ANTISIL FAST

Make sure the surface is air dried rather than wiped dry



Make sure you always use appropriate face protection and good ventilation

Product Application: »» Apply 2 to three light coata on the inside and outside bottom parts of the car body.



Shake well before using



2-3 coats approximately 20-30 microns



Dust free 10min at 23 °C



Spray at a distance of 20-30 cm thinly applied coats build up within 5-10 min intervals to achieve best results. Leave for 24 hours to harden

Flash Point:

-97°C

Specific Gravity: 0.85 g/cm³

Solid Content (No thinner): 11% Weight

VOC (2004/42/EC)

This is an aerosol product based on its ingredients and its properties. The maximum VOC content in this category is 840 g/L. The VOC content in the ready for use form of this product is 575g/L.

2004/42/IIB(e)(840)575

Theoretical Coverage:

Cleaning of equipment:

Remarks:

- Always try to use the product in accordance with the specifications provided
- It can be used by countries that do not adopt the VOC legislation as well
- · Shake thoroughly before use
- Shake for 2-3min after agitator ball has started to rattle. After preparing the area to be painted ensure it to be free from dirt, wax, oil etc. Test on a similar surface using a back and forth action
- Optimum operating temperature range 10-25°C

Shelf life:

- Up to 36 months unused spray.
- +5 to +25 °C

For professional use only. The information displayed on this sheet has been carefully selected through a series of laboratory investigations. It is based on our best knowledge at the time of issue. The data is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check for newer updates or further information if needed for his intended purpose. The intellectual property of this product, trademarks and copyrights is protected. All rights reserved. The relevant Material Safety Data Sheet and warnings displayed on the label must be read carefully. We may modify and / or discontinue operation of all or portions of this information at any time in our sole discretion, without any notice and assume no responsibility to update the information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

Issue 3 / 2015, September 2015